

SLIP RESISTANCE TEST REPORT



Project : Slip Resistance Investigation
 Location of Test : Auckland Laboratory
 Client : Fort Projects Ltd
 Slider type : FOUR-S/Slider 96, Prepared on P 400 (or equivalent) sand paper & Lapping Film
 Specimen Description : Timber Decking with Rubber Insert (Wet Pour Rubber)

Cleaning Procedure : Wet Brush
 Test Type : Unfixed
 Air Temp at Test (°C) : 21

Project Number : 1-LA491.00
 Lab Ref. Number : AL5096/1
 Client Ref. Number : -

SLIP RESISTANCE TEST RESULTS

SLIP RESISTANCE TEST RESULTS			
Specimen Nº :	Test Direction :	Mean BPN :	Mean Coefficient of Friction* :
1	N/A	50	0.54
2		45	0.47
3		47	0.50
4		45	0.47
5		45	0.47
Average SRV :		46	0.49
Classification of pedestrian surface material in accordance with table 2, AS 4586:2013 :			P4

TEST METHOD

Tests were carried out in accordance with Appendix A, AS 4586:2013, the classification is based on a test in the wet condition.

*Coefficient of friction obtained from: AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces.

SAMPLE TESTED



Tested By : G. Sandford
 Designation : Civil Engineering Technician
 Date Tested : 20/07/20

LAF026 (08/17)